



M18-078

Test panel from PSEP, France for 500h QUV-B testing. Panel designation 809

Title:
customer: PSEP, France
description: QUV-B, 500 h
sample: customer test panel 809

		809					
QUV-B (313 nm)							
Start: 13.08.18							
		60°	85°				
gloss							
	0 h	74	92				
	168 h	72	92				
	336 h	69	92				
	504 h	67	92				
0 h		X-Rite Ci 62, D65/10 SPEX					
	L	95,07					
	a	-1,11					
	b	1,08					
168 h							
	L	94,85					
	a	-1,38					
	b	2,01					
	*dE	0,99					
336 h							
	L	94,87					
	a	-1,42					
	b	2,14					
	*dE	1,12					
504 h							
	L	94,95					
	a	-1,41					
	b	2,17					
	*dE	1,14					
* dE compared to 0h value							